

Arlon 51580R015 0.015" (0.381 mm) Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction:Side 1: Uncured Silicone RubberThis data Represents typical values for the production material. The data should not be used to write, or in place of, material specifications.Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-51580R015-0015-0381-mm-Uncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Thickness	76.2 microns	3.00 mil	Polyethylene, Interleave
	178 microns	7.00 mil	Side 1
	203 microns	8.00 mil	Prime Coated 7628 Fiberglass, Substrate
	343 - 419 microns	13.5 - 16.5 mil	Overall

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 50	40 - 50	Compound Property
Tensile Strength	>= 5.52 MPa	>= 800 psi	Compound Property
Elongation at Break	>= 500 %	>= 500 %	Compound Property
Peel Strength	>= 1.05 kN/m	>= 6.00 pli	Bond Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	rated per UL card E54153
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	HB	HB	Compound Rated

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	

Processing Properties	Metric	English	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	
Shelf Life	6.00 Month @Temperature 23.9 °C	6.00 Month @Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	15.2 - 18.2	
Uncoated Fabric Break Strength	200 lb/in	Fill Direction, Substrate Property
	250 lb/in	Warp Direction, Substrate Property

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China