

Arlon 55173R045 0.045" (1.14 mm) Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: Polyethylene Layer 2: Cured Silicone Rubber Substrate: Style 162 Fiberglass Layer 1: Cured Silicone Rubber Product Use: Press Pad Appearance: Red silicone rubber on fiberglass cloth This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55173R045-0045-114-mm-Cured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	74.9 microns	2.95 mil	Interleave
	330 microns	13.0 mil	Side 1; Arlon SQA-TMS-003
	330 microns	13.0 mil	Side 2; Arlon SQA-TMS-003
	478 microns	18.8 mil	Substrate; Arlon SQA-TMS-003
	1140 microns	45.0 mil	Overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	61	61	Silicone Property; ASTM D2240
	75	75	Product Property; ASTM D2240
Tensile Strength	8.07 MPa	1170 psi	Silicone Property; ASTM D412
Elongation at Break	682 %	682 %	Silicone Property; ASTM D412

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	300 °C	572 °F	

Processing Properties	Metric	English	Comments
Shelf Life	60.0 Month	60.0 Month	From date of manufacture
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Color Descriptive Properties	Naturally White Value	Substrate Comments
	Red	
Total Product Weight (g/m2)	1665	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China