

Arlon 55279R055 0.055" (1.40 mm) Uncured/Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: Polyethylene Layer 2: Uncured Silicone Rubber Layer 1: Cured Silicone Rubber Substrate: Style 162

Fiberglass Product Use: Flexible heater insulation Appearance: Red silicone gum and rubber on fiberglass fabric This data represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55279R055-0055-140-mm-UncuredCured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	Layer 1, Silicone Property; Arlon SQA-TMS-024
	1.35 g/cc	0.0488 lb/in ³	Layer 2, Silicone Property; Arlon SQA-TMS-024
Thickness	76.2 microns	3.00 mil	Interleave
	83.8 microns	3.30 mil	Layer 2; Arlon SQA-TMS-003
	152 microns	6.00 mil	Layer 1; Arlon SQA-TMS-003
	406 microns	16.0 mil	Substrate; Arlon SQA-TMS-003
	1400 microns	55.0 mil	Overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	Layer 1, Silicone Property; ASTM D2240
	60	60	Layer 2, Silicone Property; ASTM D2240
Tensile Strength	5.52 MPa	800 psi	Layer 1, Silicone Property; ASTM D412
	5.52 MPa	800 psi	Layer 2, Silicone Property; ASTM D412
Elongation at Break	225 %	225 %	Layer 1, Silicone Property; ASTM D412
	225 %	225 %	Layer 2, Silicone Property; ASTM D412
Tear Strength	15.8 kN/m	90.0 pli	[ppiw], Layer 1, Die B, Silicone Property; ASTM D624
	15.8 kN/m	90.0 pli	[ppiw], Layer 2, Die B, Silicone Property; ASTM D624

Mechanical Properties	Metric	English	Comments
Peel Strength	1.47 kN/m	8.46 psi	(S11231), Bond Strength; Arlon SQA-TMS-011

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
UL RTI, Electrical	220 °C	428 °F	E54153
UL RTI, Mechanical without Impact	220 °C	428 °F	E54153

Electrical Properties	Metric	English	Comments
Dielectric Strength	19.3 kV/mm	490 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 121 °C	@Pressure 50.0 psi, Temperature 250 °F	
Shelf Life	6.00 Month	6.00 Month	From date of manufacture
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	56.6	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China