

Arlon 55572R030 0.030" (0.762 mm) Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction:Side 1: Cured Silicone RubberSubstrate: Style 162 Fiberglass Appearance: Red silicone rubber on fiberglass clothThis data Represents typical values for the production material. The data should not be used to write, or in place of, material specifications.Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55572R030-0030-0762-mm-Cured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	305 microns	12.0 mil	Side 1; Arlon SQA-TMS-003
	457 microns	18.0 mil	Substrate; Arlon SQA-TMS-003
	762 microns	30.0 mil	Overall; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	44	44	Silicone Property; ASTM D2240
Tensile Strength	7.58 MPa	1100 psi	Silicone Property; ASTM D412
Elongation at Break	650 %	650 %	Silicone Property; ASTM D412
Tear Strength	14.5 kN/m	83.0 pli	[ppiw], Die B, Silicone Property; ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
UL RTI, Electrical	220 °C	428 °F	E54153
UL RTI, Mechanical without Impact	200 °C	392 °F	E54153

Electrical Properties	Metric	English	Comments
Dielectric Strength	25.6 kV/mm	650 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
	120 min	2.00 hour	

Cure Time Processing Properties	Metric @ Temperature 204 °C	English @ Temperature 400 °F	Recommended Postcure Cycle Comments
Shelf Life	6.00 Month @Temperature 23.9 °C	6.00 Month @Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	29.2	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China