

Arlon 55578XA028 0.0280" Uncured/Cured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Interleave: LDPE Side 2 Layer 2: Uncured Silicone Rubber Side 2 Layer 1: Cured Silicone Rubber Substrate: Style 162 Fiberglass Side 1: Cured Silicone Rubber This data represents typical values for the production material and should not be used as material specifications. Information provided by ARLON Silicone Technologies Division.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-55578XA028-00280-UncuredCured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	Silicone Property; Arlon SQA-TMS-024
Thickness	38.1 microns	1.50 mil	Side 1; Arlon SQA-TMS-003
	50.8 microns	2.00 mil	Side 2 Layer 1; Arlon SQA-TMS-003
	216 microns	8.50 mil	Side 2 Layer 2; Arlon SQA-TMS-003
	406 microns	16.0 mil	Substrate; Arlon SQA-TMS-003
	711 microns	28.0 mil	Overall Thickness; Arlon SQA-TMS-003

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	44	44	Silicone Property; ASTM D2240
Tensile Strength	7.58 MPa	1100 psi	Silicone Property; ASTM D412
Elongation at Break	650 %	650 %	Silicone Property; ASTM D412
Peel Strength	4.82 kN/m	27.5 pli	Bond Strength (S2 to S2); Arlon SQA-TMS-011

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Inert	232 °C	450 °F	
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	18.4 kV/mm	467 kV/in	Arlon SQA-TMS-020

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	120 min Metric	2.00 hour English	Comments Recommended Post Cure Cycle
	@Temperature 204 °C	@Temperature 400 °F	
	15.0 min	0.250 hour	Recommended Cure Cycle
	@Pressure 0.345 MPa, Temperature 177 °C	@Pressure 50.0 psi, Temperature 350 °F	
Shelf Life	6.00 Month	6.00 Month	
	@Temperature 21.1 °C	@Temperature 70.0 °F	

Descriptive Properties	Value	Comments
Color	Gray	Product
	White	Substrate
Total Product Weight (oz/yd2)	28	Arlon SQA-TMS-025

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China