

Arlon 56581R025 0.025" (0.635 mm) Uncured Silicone Rubber with Fiberglass Substrate

Category : Polymer , Thermoset , Silicone , Silicone Rubber , Silicone, Molded, Glass Fiber Filled

Material Notes:

Design/Construction: Side 1: Uncured Silicone Rubber Side 2: Uncured Silicone Rubber Appearance: Red silicone gum on fiberglass cloth This data Represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-56581R025-0025-0635-mm-Uncured-Silicone-Rubber-with-Fiberglass-Substrate.php

Physical Properties	Metric	English	Comments
Thickness	76.2 microns	3.00 mil	Polyethylene, Interleave
	114 microns	4.50 mil	Side 1
	>= 114 microns	>= 4.50 mil	Side 2
	406 microns	16.0 mil	Prime Coated 1564 Fiberglass, Substrate
	660 - 686 microns	26.0 - 27.0 mil	Overall

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55 - 65	55 - 65	Compound Property
Tensile Strength	>= 6.21 MPa	>= 900 psi	Compound Property
Elongation at Break	>= 300 %	>= 300 %	Compound Property
Peel Strength	>= 1.05 kN/m	>= 6.00 pli	Bond Strength

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	220 °C	428 °F	rated per UL card E54153
Minimum Service Temperature, Air	-56.7 °C	-70.0 °F	
Flammability, UL94	HB	HB	Compound Rated

Electrical Properties	Metric	English	Comments
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
	15.0 min	0.250 hour	

Cure Time Processing Properties	Metric @ Temperature 177 °C	English @ Temperature 350 °F	Recommended Cure Cycle Comments
	120 min	2.00 hour	Recommended Postcure Cycle
	@Temperature 232 °C	@Temperature 450 °F	
Shelf Life	6.00 Month	6.00 Month	From date of manufacture
	@Temperature 23.9 °C	@Temperature 75.0 °F	

Descriptive Properties	Value	Comments
Color	Red	
Total Product Weight (oz/yd2)	25 - 31	
Uncoated Fabric Break Strength	350 lb/in	Fill Direction, Substrate Property
	400 lb/in	Warp Direction, Substrate Property

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China