

Arlon 920-05C##FR-P1 0.020" (0.508 mm) Cured Self-fusing Silicone Tape

Category: Polymer, Thermoset, Silicone

Material Notes:

Design/Construction: Interleave: Polyethylene Rubber: Cured Self-fusing Silicone Rubber Cross Section Type: 0.5" Wide Rectangular .0.5 inch wide, 20 mil thick, Black, Rectangular cross-section, Self-fusing silicone tape. Product is supplied in various roll lengths and the ## in the product number indicates roll length in yards.FAR 25.853 App.F, P.1, Aii Arlon Rectangular Tape: Rectangular tape is of uniform thickness and is ideal for applications where a smooth, even layer of tape is not required. Performance Advantages: Resists moisture, oxygen, and ozone to assure continuous high insulation values. Conforms smoothly when wrapped around complex forms. Bonds to itself at room temperature within 24 hours. Remains non-tacky to the touch and does not adhere to other surfaces, or substrates. Insulates with single wrap, thereby reducing labor time and cost. Dampens vibration and resists heat and mechanical shock as well as corona. Inherently flame resistant and when burned forms a non-conductive ash.SA & SB MOX-Tapes® provide a uniform thickness even around sharp edges. Fiberglass fabric, encapsulated inside the silicone rubber, prevents wicking and maintains high insulation resistance under high humidity conditions. These controlled stretch tapes provide a uniform insulation barrier. All tapes are protected by a special interleaved liner.Applications:Mechanical:Protection of coils from vibration.Vibration fixture, anti-scratch, and clamping pads.Harness wrapping and wire bundling, including for high temperature applications. Applied to rollers for protection and traction. Plant maintenance. Superior, heavy duty repair tape for emergency insulating barrier. Electrical: Insulation of field armature and interpole coils in large motors. Insulation for splicing and terminating of wire and cable. Insulating and sealing electrical connections. Insulating coil leads and bus bar connections. Electromagnetic coil insulation. Motor connections. Overwrapping of deteriorated insulation in reclaimed motors.Environmental:On-board aviation and space applications.Underground cable splices.Insulating heated transfer lines.Insulating in radioactive environments. Masking agent utilized in manufacturing processes and powder coatings. Insulating, protecting, and sealing rigging hardware and power systems in marine applications. This data Represents typical values for the production material. The data should not be used to write, or in place of, material specifications. Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-920-05CFR-P1-0020-0508-mm-Cured-Self-fusing-Silicone-Tape.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in³	Silicone Property; Arlon SQA-TMS- 024
Water Absorption	1.0 %	1.0 %	Arlon SQA-TMS-016
Thickness	63.5 microns	2.50 mil	Polyethylene, Interleave
	508 microns	20.0 mil	Overall; Arlon SQA-TMS-012

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	Silicone Property; Arlon SQA-TMS- 014
Tensile Strength	7.674 MPa	1113 psi	Silicone Property; Arlon SQA-TMS- 009
	462 %	462 %	Silicone Property; Arlon SQA-TMS-



Elongation at Break Mechanical Properties	Metric	English	Comments
Peel Strength	0.596 kN/m	3.40 pli	Bond Strength; Arlon- SQA-TMS-015

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	95.6 °C	204 °F	
Minimum Service Temperature, Air	-47.8 °C	-54.0 °F	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Dielectric Strength	27.6 kV/mm	701 kV/in	Arlon- SQA-TMS-020

Processing Properties	Metric	English	Comments	
Shelf Life	12.0 Month	12.0 Month	From date of manufacture	
Silen Life	@Temperature 21.1 °C	@Temperature 70.0 °F	rioni date oi mandiacture	

Descriptive Properties	Value	Comments
Color	Brown	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China