

Arlon 940-07Rxx-P1 0.040" (1.02 mm) Self-Fusing Silicone Tape

Category : Polymer , Thermoset , Silicone

Material Notes:

Design/Construction:Cross Section Type: RectangularWidth, inches: 0.75**Performance Advantages:**Resists moisture, oxygen, and ozone to assure continuous high insulation values.Conforms smoothly when wrapped around complex forms.Bonds to itself at room temperature within 24 hours.Remains non-tacky to the touch and does not adhere to other surfaces, or substrates.Insulates with single wrap, thereby reducing labor time and cost.Dampens vibration and resists heat and mechanical shock as well as corona.Inherently flame resistant and when burned forms a non-conductive ash.SA & SB MOX-Tapes® provide a uniform thickness even around sharp edges. Fiberglass fabric, encapsulated inside the silicone rubber, prevents wicking and maintains high insulation resistance under high humidity conditions. These controlled stretch tapes provide a uniform insulation barrier.All tapes are protected by a special interleaved

liner.**Applications:****Mechanical:**Protection of coils from vibration.Vibration fixture, anti-scratch, and clamping pads.Harness wrapping and wire bundling, including for high temperature applications.Applied to rollers for protection and traction.Plant maintenance.Superior, heavy duty repair tape for emergency insulating barrier.**Electrical:**Insulation of field armature and interpole coils in large motors.Insulation for splicing and terminating of wire and cable.Insulating and sealing electrical connections.Insulating coil leads and bus bar connections.Electromagnetic coil insulation.Motor connections.Overwrapping of deteriorated insulation in reclaimed

motors.**Environmental:**On-board aviation and space applications.Underground cable splices.Insulating heated transfer lines.Insulating in radioactive environments.Masking agent utilized in manufacturing processes and powder coatings.Insulating, protecting, and sealing rigging hardware and power systems in marine applications.This data Represents typical values for the production material. The data should not be used to write, or in place of, material specifications.Information provided by Arlon, Silicone Technologies Division

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-940-07Rxx-P1-0040-102-mm-Self-Fusing-Silicone-Tape.php

Physical Properties	Metric	English	Comments
Thickness	76.2 microns	3.00 mil	Polyethylene Carrier, Interleave
	940 - 1090 microns	37.0 - 43.0 mil	Overall
	17460 - 20640 microns	687.5 - 812.5 mil	Width

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 4.83 MPa	>= 700 psi	Product Property
	>= 4.83 MPa	>= 700 psi	Compound Property
Elongation at Break	>= 300 %	>= 300 %	Product Property
	>= 300 %	>= 300 %	Compound Property
Peel Strength	>= 0.351 kN/m	>= 2.00 pli	Government Bond

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Maximum Service Temperature, Air Thermal Properties	204 °C Metric	400 °F English	Comments
Minimum Service Temperature, Air	-51.1 °C	-60.0 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 3.00e+14 ohm-cm	>= 3.00e+14 ohm-cm	
Dielectric Strength	>= 15.7 kV/mm	>= 400 kV/in	

Processing Properties	Metric	English	Comments
Shelf Life	12.0 Month @Temperature 23.9 °C	12.0 Month @Temperature 75.0 °F	From date of manufacture

Descriptive Properties	Value	Comments
Color	Red	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China