

Arlon AD300A Glass, PTFE and Micro-Dispersed Ceramic

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE

Material Notes:

Lower Loss and Improved Performance over Traditional AD Series. Information provided by Arlon Materials for Electronics (MED).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Arlon-AD300A-Glass-PTFE-and-Micro-Dispersed-Ceramic.php

Physical Properties	Metric	English	Comments
Density	2.10 g/cc	0.0759 lb/in ³	
Water Absorption	0.020 %	0.020 %	

Mechanical Properties	Metric	English	Comments
Peel Strength	2.28 kN/m	13.0 pli	

Thermal Properties	Metric	English	Comments
CTE, linear	12.0 $\mu\text{m}/\text{m}\cdot\text{C}$	6.67 $\mu\text{in}/\text{in}\cdot\text{F}$	x direction
	12.0 $\mu\text{m}/\text{m}\cdot\text{C}$	6.67 $\mu\text{in}/\text{in}\cdot\text{F}$	y direction
CTE, linear, Transverse to Flow	125 $\mu\text{m}/\text{m}\cdot\text{C}$	69.4 $\mu\text{in}/\text{in}\cdot\text{F}$	z direction
Thermal Conductivity	0.320 W/m-K	2.22 BTU-in/hr-ft ² -F	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.0	3.0	
	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	
	3.0	3.0	
	@Thickness 0.508 mm	@Thickness 0.0200 in	
	3.0	3.0	
	@Thickness 3.17 mm	@Thickness 0.125 in	
Dissipation Factor	0.0020	0.0020	
	@Frequency 1.00e+10 Hz	@Frequency 1.00e+10 Hz	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Temperature Coefficient of Dielectric (ppm/°C)
Descriptive Properties

-110
Value

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China