

## Asahi Kasei Tenac® 4010 Homopolymer Acetal Resin

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Homopolymer, Unreinforced, Impact Grade

### Material Notes:

General purpose grade, high impact, high elongation, medium viscosity  
Information provided by Asahi Kasei Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Asahi-Kasei-Tenac-4010-Homopolymer-Acetal-Resin.php](http://www.lookpolymers.com/polymer_Asahi-Kasei-Tenac-4010-Homopolymer-Acetal-Resin.php)

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	Asahi Kasei Method
Melt Flow	10 g/10 min	10 g/10 min	ISO 1133 D

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	72.0 MPa	10400 psi	ISO 527 - 1 & - 2
Elongation at Break	50 %	50 %	ISO 527 - 1 & - 2
Tensile Modulus	3.20 GPa	464 ksi	ISO 527 - 1 & - 2
Charpy Impact, Notched	1.00 J/cm <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	ISO 179 / 1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	165 °C	329 °F	ISO 75 - 1 & -2 flat
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	ISO 75 - 1 & -2 flat
Flammability, UL94	HB	HB	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China