

Asahi Kasei Tenac®-C 3510 Copolymer Acetal Resin

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Impact Modified

Material Notes:

High-impact, high elongation grade, with increased molecular weight Information provided by Asahi Kasei Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Tenac-C-3510-Copolymer-Acetal-Resin.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.016 - 0.020 cm/cm	0.016 - 0.020 in/in	Asahi Kasei Method
Melt Flow	2.8 g/10 min	2.8 g/10 min	ISO 1133 D

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	63.0 MPa	9140 psi	ISO 527 - 1 & - 2
Elongation at Break	60 %	60 %	ISO 527 - 1 & - 2
Tensile Modulus	2.65 GPa	384 ksi	ISO 527 - 1 & - 2
Charpy Impact, Notched	0.900 J/cm ²	4.28 ft-lb/in ²	ISO 179 / 1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	156 °C	313 °F	ISO 75 - 1 & -2 flat
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	ISO 75 - 1 & -2 flat
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China