

Asahi Kasei Tenac®-C EF750 Acetal Copolymer, Antistat (discontinued **)

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Antistatic grade containing special carbon black. Applications: Parts requiring antistatic properties. This product is not a part of the standard product line dated 2003.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Tenac-C-EF750-Acetal-Copolymer-Antistat-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ASTM D792
Water Absorption	0.20 %	0.20 %	ASTM D570
Linear Mold Shrinkage	0.016 - 0.020 cm/cm	0.016 - 0.020 in/in	Asahi Chemical test
Melt Flow	10 g/10 min	10 g/10 min	melt index; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ASTM D785
Tensile Strength, Ultimate	51.0 MPa	7400 psi	5 mm/min; parallel to flow; ASTM D638
Elongation at Break	15 %	15 %	5 mm/min; parallel to flow; ASTM D638
Flexural Yield Strength	87.0 MPa	12600 psi	ASTM D790
Flexural Modulus	2.79 GPa	405 ksi	ASTM D790
Izod Impact, Notched	0.390 J/cm	0.731 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	100 µm/m-°C	55.6 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	162 °C	324 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 200 °C	356 - 392 °F	Resin temp

Processing Properties

Metric ^{10.0 °C}

English ^{75 °F}

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China