

Asahi Kasei Tenac® GT525 Acetal Homopolymer, 25% Glass Beads (discontinued **)

Category : Polymer , Thermoplastic , Acetal (POM)

Material Notes:

25% glass beads-filled grade with superior isotropic dimensional stability. Applications: Speedometer frames. This product is not a part of the standard product line dated 2003.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Tenac-GT525-Acetal-Homopolymer-25-Glass-Beads-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.58 g/cc	0.0571 lb/in ³	ASTM D792
Water Absorption	0.20 %	0.20 %	ASTM D570
Linear Mold Shrinkage	0.018 - 0.022 cm/cm	0.018 - 0.022 in/in	Asahi Chemical test
Melt Flow	15 g/10 min	15 g/10 min	melt index; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	92	92	ASTM D785
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Ultimate	52.0 MPa	7540 psi	5 mm/min; parallel to flow; ASTM D638
Elongation at Break	10 %	10 %	5 mm/min; parallel to flow; ASTM D638
Flexural Yield Strength	93.0 MPa	13500 psi	ASTM D790
Flexural Modulus	3.90 GPa	566 ksi	ASTM D790
Izod Impact, Notched	0.390 J/cm	0.731 ft-lb/in	ASTM D256
Taber Abrasion, mg/1000 Cycles	23	23	ASTM D1044

Thermal Properties	Metric	English	Comments
CTE, linear	70.0 µm/m-°C	38.9 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	172 °C	342 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	150 °C	302 °F	ASTM D648
Flammability, UL94	HB	HB	

Thermal Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Processing Temperature	190 - 210 °C	374 - 410 °F	Cylinder temp
Mold Temperature	60.0 - 120 °C	140 - 248 °F	
Drying Temperature	89.0 - 90.0 °C	192 - 194 °F	Drying generally not required. If it is required, drying at 80-90°C for 3-4 hours will suffice.
Dry Time	3 - 4 hour	3 - 4 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China