

## Asahi Kasei Thermylene® P-10TC-1777 10% Talc Filled, UV Stabilized Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

**Material Notes:**

Information provided by Asahi Thermofil

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Asahi-Kasei-Thermylene-P-10TC-1777-10-Talc-Filled-UV-Stabilized-Polypropylene.php](http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P-10TC-1777-10-Talc-Filled-UV-Stabilized-Polypropylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	ASTM D792
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.1 MPa	3500 psi	ASTM D638
Flexural Strength	32.4 MPa	4700 psi	ASTM D790
Flexural Modulus	1.24 GPa	180 ksi	ASTM D790
Izod Impact, Notched	13.3 J/cm	25.0 ft-lb/in	ASTM D256

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China