

Asahi Kasei Thermylene® P-20TC-0736 20% Talc Filled, Heat Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Talc Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P-20TC-0736-20-Talc-Filled-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Melt Flow	20 g/10 min	20 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	22.1 MPa	3200 psi	ASTM D638
Flexural Strength	31.0 MPa	4500 psi	ASTM D790
Flexural Modulus	1.52 GPa	220 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256
Izod Impact, Unnotched	8.54 J/cm	16.0 ft-lb/in	ASTM D4812

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China