

## Asahi Kasei Thermylene® P-30FG-0812 30% Glass Fiber Reinforced, UV Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Glass Fiber Filler

**Material Notes:**

Information provided by Asahi Thermofil

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Asahi-Kasei-Thermylene-P-30FG-0812-30-Glass-Fiber-Reinforced-UV-Stabilized.php](http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P-30FG-0812-30-Glass-Fiber-Reinforced-UV-Stabilized.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955
Melt Flow	2.0 g/10 min	2.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	93	93	ASTM D785
Tensile Strength, Yield	72.4 MPa	10500 psi	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Tensile Modulus	4.83 GPa	700 ksi	ASTM D638
Flexural Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	5.03 GPa	730 ksi	ASTM D790
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	ASTM D256
Izod Impact, Unnotched	1.60 J/cm	3.00 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	37.8 $\mu\text{m}/\text{m}\cdot\text{°C}$	21.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	154 °C	310 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	149 °C	300 °F	ASTM D648
Flammability, UL94	HB	HB	0.0591 in thickness

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China