

Asahi Kasei Thermylene® P6-10FG-0100 10% Glass Fiber Reinforced, Heat Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Glass Fiber Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P6-10FG-0100-10-Glass-Fiber-Reinforced-Heat-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	ASTM D955
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	92	92	ASTM D785
Tensile Strength, Yield	55.2 MPa	8000 psi	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Strength	72.4 MPa	10500 psi	ASTM D790
Flexural Modulus	2.14 GPa	310 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.74 J/cm	7.00 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	54.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	30.0 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM D696
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	143 $^{\circ}\text{C}$	290 $^{\circ}\text{F}$	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 $^{\circ}\text{C}$	270 $^{\circ}\text{F}$	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China