

Asahi Kasei Thermylene® P6-16FG-0801 16% Fiber Glass Reinforced, UV Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P6-16FG-0801-16-Fiber-Glass-Reinforced-UV-Stabilized.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.02 g/cc	1.02 g/cc	ASTM D792
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	ASTM D638
Flexural Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	68.9 °C	156 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China