

## Asahi Kasei Thermylene® P6-20FG-0600 20% Glass Fiber Reinforced, Heat Stabilized

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

**Material Notes:**

Information provided by Asahi Thermofil

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Asahi-Kasei-Thermylene-P6-20FG-0600-20-Glass-Fiber-Reinforced-Heat-Stabilized.php](http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P6-20FG-0600-20-Glass-Fiber-Reinforced-Heat-Stabilized.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	94	94	ASTM D785
Tensile Strength, Yield	68.9 MPa	10000 psi	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Flexural Strength	96.5 MPa	14000 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.27 J/cm	8.00 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	43.2 $\mu\text{m}/\text{m}\cdot\text{°C}$	24.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	154 °C	310 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	146 °C	295 °F	ASTM D648
Flame Spread	25 mm/min	1.0 in/min	Horizontal Burn Rate; FMVSS302

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China