

Asahi Kasei Thermylene® P6-20FG-0738 20% Glass Fiber Reinforced, High Impact

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

Material Notes:

Information provided by Asahi Thermofil

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asahi-Kasei-Thermylene-P6-20FG-0738-20-Glass-Fiber-Reinforced-High-Impact.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	94	94	ASTM D785
Tensile Strength, Yield	53.1 MPa	7700 psi	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Strength	72.4 MPa	10500 psi	ASTM D790
Flexural Modulus	2.90 GPa	420 ksi	ASTM D790
Izod Impact, Notched	1.82 J/cm	3.40 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.41 J/cm	12.0 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear	43.2 $\mu\text{m}/\text{m}\cdot\text{°C}$	24.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	152 °C	305 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	136 °C	277 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China