

## Asahi Kasei Xyron® X0700 Modified Polyphenylene Ether

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polyphenylene Ether, Molded

### Material Notes:

Automotive Information provided by Asahi Kasei

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Asahi-Kasei-Xyron-X0700-Modified-Polyphenylene-Ether.php](http://www.lookpolymers.com/polymer_Asahi-Kasei-Xyron-X0700-Modified-Polyphenylene-Ether.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.06 g/cc	1.06 g/cc	23°C; ASTM D792
Moisture Absorption	0.100 %	0.100 %	23°C, 50% RH 24 hours; ASTM D570
Linear Mold Shrinkage	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	41.0 MPa	5950 psi	23°C, 50% RH; ASTM D638
Elongation at Break	60 %	60 %	23°C, 50% RH; ASTM D638
Flexural Strength	70.0 MPa	10200 psi	23°C, 50% RH; ASTM D790
Flexural Modulus	2.12 GPa	307 ksi	23°C, 50% RH; ASTM D790
Izod Impact, Notched	1.96 J/cm @Thickness 6.40 mm, Temperature 23.0 °C	3.67 ft-lb/in @Thickness 0.252 in, Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	75.0 µm/m-°C @Temperature -30.0 - 60.0 °C	41.7 µin/in-°F @Temperature -22.0 - 140 °F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ASTM D648
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	Equivalent
	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	Equivalent

Processing Properties	Metric	English	Comments
Processing Temperature	220 - 250 °C	428 - 482 °F	Resin Temperature

Mold Temperature Processing Properties	50.0 - 80.0 °C Metric	122 - 176 °F English	Comments
Drying Temperature	90.0 - 100 °C	194 - 212 °F	Pre-drying Temperature
Dry Time	2 - 4 hour	2 - 4 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China