

Ascend Performance Materials Vydyne® 20NSP BLK Nylon 66, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Nucleated

Material Notes:

Vydyne® 20NSP BLK is a general-purpose, high nucleated, lubricated PA66 resin. Available in black, it is designed to crystallize rapidly in order to reduce cycle times and increase productivity through faster part set-up. The higher crystalline structure will increase tensile modulus and strength, reduce elongation and may slightly lower mold shrinkage when compared to standard general-purpose non nucleated PA66. The rapid crystallization of Vydyne 20NSP BLK resin may allow part ejection at a higher temperature compared to general-purpose PA66. Critical factors unique to each application such as mold design, part design, tolerances and other factors will dictate ultimate cycle time benefits. It is recommended to check critical part dimensions against specifications before adopting shorter molding cycles. Vydyne 20NSP BLK resin has an external lubricant for improved machine feed and an internal lubricant for improved mold release.

Typical Applications/End Uses: End uses for Vydyne 20NSP BLK include terminal blocks, bears, control cams, electrical connectors, housings, cable ties, fasteners, switch components and industrial parts that require chemical resistance, stiffness, wear resistance and rigidity.

Availability: Asia Pacific Europe North America Additive: Lubricant Nucleating Agent Features: Fast Molding Cycle General Purpose Good Mold Release Good Stiffness High Rigidity Lubricated Nucleated Uses: Bearings Cams Connectors Fasteners General Purpose Housings Industrial Applications Appearance: Black Forms: Pellets Processing Method: Injection Molding Information provided by Ascend Performance Materials.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ascend-Performance-Materials-Vydyne-20NSP-BLK-Nylon-66-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ISO 1183
Water Absorption	1.2 % @Time 86400 sec	1.2 % @Time 24.0 hour	ISO 62
Moisture Absorption at Equilibrium	2.4 %	2.4 %	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.014 cm/cm @Diameter 2.00 mm	0.014 in/in @Diameter 0.0787 in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.016 cm/cm @Diameter 2.00 mm	0.016 in/in @Diameter 0.0787 in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 MPa	7250 psi	ISO 527-2
Tensile Strength, Yield	60.0 MPa	8700 psi	ISO 527-2
Elongation at Break	20 %	20 %	ISO 527-2
Elongation at Yield	15 %	15 %	ISO 527-2

Tensile Modulus Mechanical Properties	2.50 GPa Metric	363 ksi English	ISO 527-2 Comments
Flexural Strength	35.0 MPa	5080 psi	ISO 178
Flexural Modulus	1.30 GPa	189 ksi	ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m ² @Temperature -30.0 °C	2.38 ft-lb/in ² @Temperature -22.0 °F	ISO 180
	15.0 kJ/m ² @Temperature 23.0 °C	7.14 ft-lb/in ² @Temperature 73.4 °F	ISO 180
Charpy Impact Unnotched	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	ISO 179/1eU
	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	0.500 J/cm ² @Temperature -30.0 °C	2.38 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eA
	1.50 J/cm ² @Temperature 23.0 °C	7.14 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China