

## Ascend Performance Materials Vydyn<sup>®</sup> 21FSR Nylon 66, General Purpose

Category : Polymer , Thermoplastic , Nylon , Nylon 66

**Material Notes:**

Vydyn<sup>®</sup> 21FSR is a high-viscosity, general-purpose PA66 resin. It is available in natural and designed for extrusion-compounding applications. This resin offers a well balanced combination of engineering properties characterized by high strength, rigidity, good toughness, high melt point, good surface lubricity and abrasion resistance. Vydyn 21FSR maintains the chemical resistance typical of PA66 to many chemicals, machine and motor oils, solvents and gasoline. Typical Applications/End Uses: CompoundingAvailability:Asia PacificEuropeNorth AmericaFeatures:Gasoline ResistanceGeneral PurposeGood Abrasion ResistanceGood Chemical ResistanceGood ToughnessHigh RigidityHigh StrengthLow Viscosity Oil ResistantSolvent ResistantUses:CompoundingGeneral PurposeAppearance: Natural ColorForms: PelletsProcessing Method: Compounding and Compounding ExtrusionInformation provided by Ascend

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ascend-Performance-Materials-Vydyn-21FSR-Nylon-66-General-Purpose.php](http://www.lookpolymers.com/polymer_Ascend-Performance-Materials-Vydyn-21FSR-Nylon-66-General-Purpose.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ISO 1183
Bulk Density	0.674 g/cc	0.0243 lb/in <sup>3</sup>	ASTM D1895
Relative Viscosity	48 - 54 cP	48 - 54 cP	ASTM D789
Viscosity Measurement	143 - 153	143 - 153	sulfuric acid; ISO 307

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	ISO 11357

Optical Properties	Metric	English	Comments
Yellow Index	4.0 %	4.0 %	ASTM D1925

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.50 %	<= 0.50 %	ASTM D789

Descriptive Properties	Value	Comments
RV, Formic Acid, ASTM D789	48-54	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China