

Ascend Performance Materials Vydyne® 909 Nylon 66/6, 25% Glass Reinforced, Ignition Resistant, Conditioned

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66 , Nylon 66/6 , 30% Glass Fiber Reinforced

Material Notes:

Vydyne® 909 is halogenated, 25% glass-filled, flame-retardant PA66/6 copolymer with excellent strength and toughness. It is lubricated for machine feed and easy mold release and has an Underwriters Laboratories UL 94 flammability classification of V-0 at 0.4 mm (0.016") thick. Availability: Asia Pacific Europe North America Additive: Halogen Lubricant Features: Good Crack Resistance Good Mold Release Good Toughness Halogenated High Rigidity High Strength Ignition Resistance Lubricated Uses: Appliances Automotive Electronics Bobbins Connectors Electrical Housing Electrical Parts Electrical/Electronic Applications Fasteners Industrial Applications Lighting Applications Living Hinges Printed Circuit Boards Switches Appearance: Natural Color Forms: Pellets Processing Method: Injection Molding Information provided by Ascend

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ascend-Performance-Materials-Vydyne-909-Nylon-666-25-Glass-Reinforced-Ignition-Resistant-Conditioned.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.47 g/cc	1.47 g/cc	ISO 1183
Water Absorption	0.70 %	0.70 %	24 hrs; ISO 62
Moisture Absorption at Equilibrium	1.3 %	1.3 %	50%rh; ISO 62
Linear Mold Shrinkage	0.0040 cm/cm @Thickness 2.00 mm	0.0040 in/in @Thickness 0.0787 in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.010 cm/cm @Thickness 2.00 mm	0.010 in/in @Thickness 0.0787 in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	90.0 MPa	13100 psi	ISO 527-2
Elongation at Break	3.0 %	3.0 %	ISO 527-2
Tensile Modulus	7.10 GPa	1030 ksi	ISO 527-2
Flexural Strength	140 MPa	20300 psi	ISO 178
Flexural Modulus	5.00 GPa	725 ksi	ISO 178

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China