

Ascend Performance Materials Vydyne® R525H Nat Nylon 66, 25% Glass Reinforced, DAM

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Vydyne® R525H Nat is hydrolysis-resistant, 25% glass-fiber reinforced, heat-stabilized PA66 resin. Available in natural, it is specifically designed to maximize the retention of physical properties when exposed to anti-freeze solutions at elevated temperatures. This product is lubricated for improved machine feed and flow. Glass-reinforced Vydyne resins provide higher heat distortion temperature, resistance to creep and better dimensional stability when compared with unreinforced PA66. These products have good chemical resistance to a broad range of chemicals including gasoline, hydraulic fluids and most solvents. Vydyne R525H Nat is heat-stabilized to minimize oxidative degradation of the polymer when exposed to elevated temperatures in service. This product provides improved retention of physical properties under exposure to long-term heat. Also, Vydyne R525H Nat has excellent knit-line strength and fatigue resistance, which is essential for cycle testing with anti-freeze solutions. Availability:Asia PacificEuropeNorth AmericaFiller/Reinforcement:Glass Fiber, 25% Filler by WeightAdditive:Heat StabilizerLubricant Features: Antifreeze ResistantFatigue ResistantGasoline ResistanceGood Chemical ResistanceHigh FlowHeat Stabilized Lubricated Solvent ResistantUses: Automotive Under the Hood Appearance: Natural ColorForms: PelletsProcessing Method: Injection MoldingInformation provided by Ascend Performance Materials.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ascend-Performance-Materials-Vydyne-R525H-Nat-Nylon-66-25-Glass-Reinforced-DAM.php

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in ³	ISO 1183
Water Absorption	0.90 % @Time 86400 sec	0.90 % @Time 24.0 hour	ISO 62
Moisture Absorption at Equilibrium	2.0 %	2.0 %	50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Diameter 2.00 mm	0.0040 in/in @Diameter 0.0787 in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0090 cm/cm @Diameter 2.00 mm	0.0090 in/in @Diameter 0.0787 in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	174 MPa	25200 psi	ISO 527-2
Elongation at Break	3.0 %	3.0 %	ISO 527-2
Tensile Modulus	8.60 GPa	1250 ksi	ISO 527-2
Flexural Strength	250 MPa	36300 psi	ISO 178
Flexural Modulus	7.70 GPa	1120 ksi	ISO 178

Poissons Ratio Mechanical Properties	0.40 Metric	0.40 English	ISO 527-2 Comments
Izod Impact, Notched (ISO)	9.00 kJ/m ²	4.28 ft-lb/in ²	ISO 180
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	10.0 kJ/m ²	4.76 ft-lb/in ²	ISO 180
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	5.50 J/cm ²	26.2 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.50 J/cm ²	30.9 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.10 J/cm ²	5.23 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	2.50 µm/m-°C	1.39 µin/in-°F	ISO 11359-2
	@Thickness 2.00 mm, Temperature 23.0 - 55.0 °C	@Thickness 0.0787 in, Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	11.0 µm/m-°C	6.11 µin/in-°F	ISO 11359-2
	@Thickness 2.00 mm, Temperature 23.0 - 55.0 °C	@Thickness 0.0787 in, Temperature 73.4 - 131 °F	
Melting Point	260 °C	500 °F	ISO 11357-3
Deflection Temperature at 0.46 MPa (66 psi)	258 °C	496 °F	Unannealed; ISO 75-2/B
Deflection Temperature at 1.8 MPa (264 psi)	245 °C	473 °F	Unannealed; ISO 75-2/A
UL RTI, Electrical	140 °C	284 °F	UL 746
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	140 °C	284 °F	UL 746
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	140 °C	284 °F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
	120 °C	248 °F	

UL RTI, Mechanical with Impact Thermal Properties	Metric @Thickness 0.750 mm	English @Thickness 0.0295 in	UL 746 Comments
	120 °C @Thickness 1.50 mm	248 °F @Thickness 0.0591 in	UL 746
	120 °C @Thickness 3.00 mm	248 °F @Thickness 0.118 in	UL 746
UL RTI, Mechanical without Impact	125 °C @Thickness 0.750 mm	257 °F @Thickness 0.0295 in	UL 746
	140 °C @Thickness 1.50 mm	284 °F @Thickness 0.0591 in	UL 746
	140 °C @Thickness 3.00 mm	284 °F @Thickness 0.118 in	UL 746
Flammability, UL94	HB @Thickness 0.750 mm	HB @Thickness 0.0295 in	
	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	
	HB @Thickness 3.00 mm	HB @Thickness 0.118 in	
Glow Wire Test	675 °C @Thickness 0.750 mm	1250 °F @Thickness 0.0295 in	Flammability Index; IEC 60695-2-12
	675 °C @Thickness 1.50 mm	1250 °F @Thickness 0.0591 in	Flammability Index; IEC 60695-2-12
	675 °C @Thickness 3.00 mm	1250 °F @Thickness 0.118 in	Flammability Index; IEC 60695-2-12
	700 °C @Thickness 0.750 mm	1290 °F @Thickness 0.0295 in	Ignition Temperature; IEC 60695-2-13
	700 °C @Thickness 1.50 mm	1290 °F @Thickness 0.0591 in	Ignition Temperature; IEC 60695-2-13
	700 °C @Thickness 3.00 mm	1290 °F @Thickness 0.118 in	Ignition Temperature; IEC 60695-2-13

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	1.00e+13 ohm-cm Metric	1.00e+13 ohm-cm English	Comments
Volume Resistivity	@Thickness 0.750 mm	@Thickness 0.0295 in	IEC 60093
Dielectric Strength	20.0 kV/mm @Thickness 1.00 mm	508 kV/in @Thickness 0.0394 in	IEC 60243
Arc Resistance	60 - 119 sec @Thickness 3.00 mm	60 - 119 sec @Thickness 0.118 in	ASTM D495
Comparative Tracking Index	250 - 399 V @Thickness 3.00 mm	250 - 399 V @Thickness 0.118 in	IEC 60112
Hot Wire Ignition, HWI	7.0 - 14 sec @Thickness 0.750 mm	7.0 - 14 sec @Thickness 0.0295 in	UL 746
	7.0 - 14 sec @Thickness 3.00 mm	7.0 - 14 sec @Thickness 0.118 in	UL 746
	15 - 29 sec @Thickness 1.50 mm	15 - 29 sec @Thickness 0.0591 in	UL 746
High Amp Arc Ignition, HAI	>= 120 arcs @Thickness 0.750 mm	>= 120 arcs @Thickness 0.0295 in	UL 746
	>= 120 arcs @Thickness 1.50 mm	>= 120 arcs @Thickness 0.0591 in	UL 746
	>= 120 arcs @Thickness 3.00 mm	>= 120 arcs @Thickness 0.118 in	UL 746
High Voltage Arc-Tracking Rate, HVTR	10.1 - 25.4 mm/min	0.398 - 1.00 in/min	UL 746

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	280 - 310 °C	536 - 590 °F	
Middle Barrel Temperature	280 - 310 °C	536 - 590 °F	
Front Barrel Temperature	280 - 310 °C	536 - 590 °F	
Nozzle Temperature	280 - 310 °C	536 - 590 °F	
Melt Temperature	285 - 305 °C	545 - 581 °F	
Mold Temperature	65.0 - 95.0 °C	149 - 203 °F	
Drying Temperature	80.0 °C	176 °F	

Dry Time Processing Properties	4.00 hour Metric	4.00 hour English	Comments
Descriptive Properties		Value	Comments
Suggested Max Regrind		25 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China