

## Ashley Polymers Ashlene® 195-N2 Acetal

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

### Material Notes:

A general purpose, medium viscosity natural.Data provided by the manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ashley-Polymers-Ashlene-195-N2-Acetal.php](http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-195-N2-Acetal.php)

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.22 %	0.22 %	ASTM D570
Linear Mold Shrinkage	0.022 cm/cm	0.022 in/in	ASTM D955
Melt Flow	27 g/10 min	27 g/10 min	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ASTM D785
Tensile Strength, Ultimate	62.0 MPa	8990 psi	ATSM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Strength	91.0 MPa	13200 psi	ASTM D790
Flexural Modulus	2.60 GPa	377 ksi	ASTM D790
Shear Strength	55.0 MPa	7980 psi	ASTM D732
Izod Impact, Notched	0.540 J/cm	1.01 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	165 °C	329 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	158 °C	316 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ASTM D648
Flammability, UL94	HB @Thickness 0.800 mm	HB @Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.7	3.7	ASTM D150

Electrical Properties	@Frequency 1e+6 Hz Metric	@Frequency 1e+6 Hz English	Comments
Dissipation Factor	0.0070	0.0070	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China