

Ashley Polymers Ashlene® 527LD Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Impact Grade

Material Notes:

A very high impact, slightly lubricated nylon resin.Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-527LD-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in³	ASTM D792
Water Absorption	1.3 %	1.3 %	ASTM D570
Linear Mold Shrinkage	0.0015 cm/cm	0.0015 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	113	113	ASTM D785
Tensile Strength, Yield	51.0 MPa	7400 psi	ASTM D638
Elongation at Break	55 %	55 %	ASTM D638
Flexural Modulus	1.70 GPa	247 ksi	ASTM D790
Izod Impact, Notched	10.13 J/cm	18.98 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	254 °C	489 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	213 °C	415 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	68.0 °C	154 °F	ASTM D648

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Constant	2.9 @Frequency 1e+6 Hz	2.9 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	18.0 kV/mm	457 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China