

## Ashley Polymers Ashlene® 528L2 Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66 , Unreinforced

### Material Notes:

A general purpose highly lubricated Nylon 66 resin.Data provided by the manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ashley-Polymers-Ashlene-528L2-Nylon-66.php](http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-528L2-Nylon-66.php)

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.5 %	1.5 %	24 hrs; ASTM D570
Water Absorption at Saturation	9.0 %	9.0 %	ASTM D570
Linear Mold Shrinkage	0.015 cm/cm	0.015 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	119	119	ASTM D785
Tensile Strength, Ultimate	81.5 MPa	11800 psi	ATSM D638
Elongation at Break	50 %	50 %	ASTM D638
Elongation at Yield	5.0 %	5.0 %	ASTM D638
Flexural Strength	90.0 MPa	13100 psi	ASTM D790
Flexural Modulus	2.70 GPa	392 ksi	ASTM D790
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	252 °C	486 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	235 °C	455 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	ASTM D648

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Constant	3.1	3.1	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Dielectric Strength Electrical Properties	25.0 kV/mm Metric	635 kV/in English	ASTM D149 Comments
--	----------------------	----------------------	-----------------------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China