

## Ashley Polymers Ashlene® 79MGS Nylon 6, 40% Glass Mineral reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Glass/Mineral Reinforced

### Material Notes:

A 40% glass mineral reinforced Nylon 6 with good dimensional stability, stiffness, sink and warp resistance. Modified for improved surface appearance. Data provided by the manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ashley-Polymers-Ashlene-79MGS-Nylon-6-40-Glass-Mineral-reinforced.php](http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-79MGS-Nylon-6-40-Glass-Mineral-reinforced.php)

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.090 %	0.090 %	24 hrs; ASTM D570
Moisture Absorption at Equilibrium	1.5 %	1.5 %	50% RH; ASTM D570
Water Absorption at Saturation	4.0 %	4.0 %	ASTM D570
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Yield	127 MPa	18400 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Modulus	7.80 GPa	1130 ksi	ASTM D790
Izod Impact, Notched	0.480 J/cm	0.899 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	218 °C	424 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	216 °C	421 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	199 °C	390 °F	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Constant	3.7	3.7	ASTM D150

Electrical Properties	@Frequency 1e+6 Hz Metric	@Frequency 1e+6 Hz English	Comments
Dielectric Strength	13.4 kV/mm	340 kV/in	ASTM D149

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China