Ashley Polymers Ashlene® 859 Nylon 6, Pellet form

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Unreinforced

Material Notes:

Ashlene 859 is offered in small pellet form. It is dried to less than 0.1% moisture eliminating the need for predrying. Ashlene 859 is molded

with wall thickness ranging from 1/16" to greater than 1".Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-859-Nylon-6-Pellet-form.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in³	ASTM D792
Water Absorption	1.8 %	1.8 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Elongation at Yield	100 %	100 %	ASTM D638
Izod Impact, Notched	0.430 J/cm	0.806 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	177 °C	351 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	74.0 °C	165 °F	ASTM D648

Contact Songhan Plastic Technology Co., Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China