

Ashley Polymers Ashlene® 925LMS-22G Nylon 12, 22% Glass Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 12 , Nylon 12, 20% Glass Fiber Filled

Material Notes:

A 22% glass reinforced, Molybdenum disulfide filled, Nylon 12 resin for injection molding. Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-925LMS-22G-Nylon-12-22-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	97.0 MPa	14100 psi	ATSM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Modulus	4.00 GPa	580 ksi	ASTM D790
Izod Impact, Notched	1.23 J/cm	2.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	185 °C	365 °F	ASTM D3418

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China