

Ashley Polymers Ashlene® D926 Nylon 12

Category : Polymer , Thermoplastic , Nylon , Nylon 12

Material Notes:

A flexible Nylon 12 with exceptional toughness, excellent abrasion and chemical resistance, outstanding low temperature performance, dimensional stability and low moisture absorption. Also available with UV stabilizer, designated D926H. Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-D926-Nylon-12.php

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in ³	ASTM D792
Water Absorption	0.20 %	0.20 %	24 hrs; ASTM D570
Water Absorption at Saturation	1.4 %	1.4 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	51.0 MPa	7400 psi	ASTM D638
Elongation at Break	325 %	325 %	ASTM D638
Flexural Modulus	0.830 GPa	120 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm	2.49 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	184 °C	363 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	132 °C	270 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	52.0 °C	126 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China