

Ashley Polymers Ashlene® L935 Nylon 11

Category : Polymer , Thermoplastic , Nylon , Nylon 11 , Nylon 11 , Unreinforced

Material Notes:

An economy grade, unplasticized Nylon 11 for extrusion applications. Also available is L935H, same with UV and heat stabilizer. Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-L935-Nylon-11.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Water Absorption	0.30 %	0.30 %	ASTM D570
Moisture Absorption at Equilibrium	1.1 %	1.1 %	65% RH; ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	105	105	ASTM D785
Tensile Strength, Ultimate	62.0 MPa	8990 psi	ATSM D638
Elongation at Break	300 %	300 %	ASTM D638
Flexural Modulus	1.20 GPa	174 ksi	ASTM D790
Izod Impact, Notched	0.910 J/cm	1.70 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	191 °C	376 °F	ASTM D3418
Deflection Temperature at 0.46 MPa (66 psi)	150 °C	302 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	46.0 °C	115 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China