

Ashley Polymers Ashlene® PC/ABS Alloy 307WO

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

General purpose flame retardant with high impact, good low temperature properties and high heat resistance. Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-PCABS-Alloy-307WO.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0050 cm/cm	0.0050 in/in	ASTM D955
High Load Melt Index	7.0 g/10 min @Load 21.6 kg, Temperature 260 °C	7.0 g/10 min @Load 47.6 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	ASTM D785
Tensile Strength, Ultimate	60.0 MPa	8700 psi	ATSM D638
Elongation at Break	105 %	105 %	ASTM D638
Flexural Strength	93.0 MPa	13500 psi	ASTM D790
Flexural Modulus	2.60 GPa	377 ksi	ASTM D790
Izod Impact, Notched	5.87 J/cm	11.0 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	112 °C	234 °F	ASTM D648
Flammability, UL94	V-0	V-0	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China