

Ashley Polymers Ashlene® PE126 PET Polyester, 30% Glass Reinforced

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 30% Glass Reinforced

Material Notes:

PET Polyester, with 30% glass reinforcement.Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-PE126-PET-Polyester-30-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.55 g/cc	0.0560 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	152 MPa	22000 psi	ASTM D638
Elongation at Break	2.2 %	2.2 %	
Flexural Strength	228 MPa	33100 psi	ASTM D790
Flexural Modulus	8.60 GPa	1250 ksi	ASTM D790
Izod Impact, Notched	0.960 J/cm	1.80 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	245 °C	473 °F	ASTM D3418
Deflection Temperature at 1.8 MPa (264 psi)	224 °C	435 °F	ASTM D648

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.5	3.5	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	22.0 kV/mm	559 kV/in	Short Time; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.021	0.021	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China