

## Ashley Polymers Ashlene® RH190H Acetal

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Homopolymer, Unreinforced

### Material Notes:

General purpose reprocessed homopolymer, excellent toughness, strength, stiffness and lubricity. UV stabilized for good weatherability.

Available in Natural and Black. Natural: Designated RH190H-N3; Black: Designated RH190HB. Data provided by the manufacturer

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Ashley-Polymers-Ashlene-RH190H-Acetal.php](http://www.lookpolymers.com/polymer_Ashley-Polymers-Ashlene-RH190H-Acetal.php)

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage, Flow	0.022 cm/cm	0.022 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.018 cm/cm	0.018 in/in	ASTM D955
Melt Flow	8.0 g/10 min	8.0 g/10 min	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	63.0 MPa	9140 psi	ASTM D638
Elongation at Break	12 %	12 %	ASTM D638
Flexural Modulus	2.70 GPa	392 ksi	ASTM D790
Izod Impact, Notched	0.590 J/cm	1.11 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	175 °C	347 °F	ASTM D3418

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China