

Asia International Enterprise (Hong Kong) ST60G6 Nylon 66, 30% Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Information provided by Asia International Enterprise (Hong Kong) Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Asia-International-Enterprise-Hong-Kong-ST60G6-Nylon-66-30-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ASTM D792
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Filler Content	30 %	30 %	
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Ultimate	196 MPa	28400 psi	5mm/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	5mm/min; ASTM D638
Flexural Strength	275 MPa	39900 psi	2.8mm/min; ASTM D790
Flexural Modulus	5.88 GPa	853 ksi	2.8mm/min; ASTM D790
Izod Impact, Notched	2.45 J/cm	4.59 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	ASTM D648
Flammability, UL94	HB	HB	

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	250 - 300 °C	482 - 572 °F	Cylinder Temperature
Mold Temperature	50.0 - 90.0 °C	122 - 194 °F	
Drying Temperature	80.0 - 90.0 °C	176 - 194 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China