

Axiall 10754 Wire & Cable Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

General purpose jacket compound. Maximum service temperature rating of 75°C. Fungus resistant. Information provided by Georgia Gulf. Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-10754-Wire-Cable-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 - 1.40 g/cc	1.36 - 1.40 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72 - 78	72 - 78	delayed; ASTM D-2240
Tensile Strength, Yield	13.69 MPa	1985 psi	ASTM D-638
Elongation at Yield	350 %	350 %	ASTM D-638
100% Modulus	0.00631 GPa	0.915 ksi	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	171 °C	340 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China