

## Axiall 10756 Wire & Cable Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

### Material Notes:

General purpose, non-lead stabilized jacketing compound recommended for a maximum service temperature of 80°C. Information provided by Georgia Gulf. Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Axiall-10756-Wire-Cable-Flexible-PVC.php](http://www.lookpolymers.com/polymer_Axiall-10756-Wire-Cable-Flexible-PVC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 - 1.40 g/cc	1.36 - 1.40 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	72 - 78	72 - 78	delayed; ASTM D-2240
Tensile Strength, Yield	17.2 MPa	2500 psi	ASTM D-638
Elongation at Yield	300 %	300 %	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	177 °C	350 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China