

Axiall 1131-57D Wire & Cable Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Non-lead stabilized 105°C rated jacket compound. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-1131-57D-Wire-Cable-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 - 1.42 g/cc	1.38 - 1.42 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	84 - 90	84 - 90	delayed; ASTM D-2240
Tensile Strength, Yield	17.2 MPa	2500 psi	ASTM D-638
Elongation at Yield	280.8 %	280.8 %	Air Aging: 136 hours @ 136°C; 30 mil slabs; UL 1581
	325 %	325 %	ASTM D-638
100% Modulus	0.0103 GPa	1.50 ksi	ASTM D-638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-20.0 °C	-4.00 °F	ASTM D-746
Oxygen Index	23 %	23 %	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	188 °C	370 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China