

Axiall 13870 Wire & Cable Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Non-lead stabilized, 720 hour sunlight resistant insulation compound recommended for TW and 75C Class 43 applications. Information provided by Georgia Gulf. Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-13870-Wire-Cable-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 - 1.38 g/cc	1.34 - 1.38 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	84 - 90	84 - 90	delayed; ASTM D-2240
Tensile Strength, Yield	17.6 MPa	2550 psi	ASTM D-638
Elongation at Yield	272.7 %	272.7 %	Air Aging: 240 hours @ 100°C; 30 mil slabs; UL 1581
	340 %	340 %	ASTM D-638
100% Modulus	0.0117 GPa	1.70 ksi	ASTM D-638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-28.0 °C	-18.4 °F	ASTM D-746
Oxygen Index	26 %	26 %	ASTM D-638

Electrical Properties	Metric	English	Comments
Volume Resistivity	9.00e+14 ohm-cm	9.00e+14 ohm-cm	50% RH; ASTM D-257

Processing Properties	Metric	English	Comments
Melt Temperature	182 °C	360 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China