

Axiall 13880 Wire & Cable Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Insulation compound suitable for 75C, oil I applications. UL recognized component for TW, Oil I and 720 hour sunlight resistant

applications.Information provided by Georgia GulfGeorgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-13880-Wire-Cable-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 - 1.43 g/cc	1.39 - 1.43 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85 - 91	85 - 91	delayed; ASTM D-2240
Tensile Strength, Yield	17.9 MPa	2600 psi	ASTM D-638
Elongation at Yield	300 %	300 %	ASTM D-638
100% Modulus	0.0117 GPa	1.70 ksi	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	182 °C	360 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China