

Axiall 15881 Wire & Cable Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

80C general purpose. 300 hour sunlight resistant. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-15881-Wire-Cable-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 - 1.40 g/cc	1.36 - 1.40 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85 - 91	85 - 91	delayed; ASTM D-2240
Tensile Strength, Yield	17.2 MPa	2500 psi	ASTM D-638
Elongation at Yield	255 %	255 %	Air Aging: 168 hours @ 113°C; 30 mil slabs; UL 1581
	300 %	300 %	ASTM D-638
100% Modulus	0.0121 GPa	1.75 ksi	ASTM D-638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-25.0 °C	-13.0 °F	ASTM D-746
Oxygen Index	23 %	23 %	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	188 °C	370 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China