

Axiall 16930 Wire & Cable Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Non-lead stabilized tray cable jacketing compound. UL recognized component for 720 hour sunlight resistance in black only. Information provided by Georgia Gulf. Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-16930-Wire-Cable-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 - 1.40 g/cc	1.36 - 1.40 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90 - 96	90 - 96	delayed; ASTM D-2240
Tensile Strength, Yield	17.9 MPa	2600 psi	ASTM D-638
Elongation at Yield	174.6 %	174.6 %	Air Aging: 168 hours @ 121°C; 50 mil die-cut from jacket; UL 1581
	300 %	300 %	ASTM D-638
100% Modulus	0.0138 GPa	2.00 ksi	ASTM D-638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-22.0 °C	-7.60 °F	ASTM D-746
Oxygen Index	30 %	30 %	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	193 °C	380 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China