

Axiall 22880 Coax & Telecom Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Flame retardant riser jacket over PVC or FR HDPE primaries. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-22880-Coax-Telecom-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.34 - 1.38 g/cc	1.34 - 1.38 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85 - 91	85 - 91	delayed; ASTM D-2240
Tensile Strength, Yield	20.0 MPa	2900 psi	ASTM D-638
Elongation at Yield	238.7 %	238.7 %	Air Aging: 10 days @ 100°C; 30 mil slabs; UL 1581
	310 %	310 %	ASTM D-638
100% Modulus	0.0124 GPa	1.80 ksi	ASTM D-638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-33.0 °C	-27.4 °F	ASTM D-746
Oxygen Index	31.5 %	31.5 %	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	185 °C	365 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China