

## Axiall 22905 Coax & Telecom Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Wire and Cable Grade

**Material Notes:**

Non-lead tray cable jacket for 75°C maximum service temperature. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Axiall-22905-Coax-Telecom-Flexible-PVC.php](http://www.lookpolymers.com/polymer_Axiall-22905-Coax-Telecom-Flexible-PVC.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 - 1.37 g/cc	1.33 - 1.37 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	87 - 93	87 - 93	delayed; ASTM D-2240
Tensile Strength, Yield	22.1 MPa	3200 psi	ASTM D-638
Elongation at Yield	320 %	320 %	ASTM D-638
100% Modulus	0.0131 GPa	1.90 ksi	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	191 °C	375 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China