

Axiall 22930 Coax & Telecom Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Jacket compound suitable for riser applications when used with flame retardant PVC primaries. Maximum service temperature of 75°C. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-22930-Coax-Telecom-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 - 1.43 g/cc	1.39 - 1.43 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90 - 96	90 - 96	delayed; ASTM D-2240
Tensile Strength, Yield	19.0 MPa	2750 psi	ASTM D-638
Elongation at Yield	300 %	300 %	ASTM D-638
100% Modulus	0.0138 GPa	2.00 ksi	ASTM D-638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-28.0 °C	-18.4 °F	ASTM D-746
Oxygen Index	32.5 %	32.5 %	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	191 °C	375 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China