

Axiall 22950 Coax & Telecom Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Riser jacket, 25 mil over HDPE primaries. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-22950-Coax-Telecom-Flexible-PVC.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------|------------------|------------|
| Specific Gravity | 1.48 - 1.52 g/cc | 1.48 - 1.52 g/cc | ASTM D-792 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|------------|----------|----------------------|
| Hardness, Shore A | 92 - 98 | 92 - 98 | delayed; ASTM D-2240 |
| Tensile Strength, Yield | 18.6 MPa | 2700 psi | ASTM D-638 |
| Elongation at Yield | 310 % | 310 % | ASTM D-638 |
| 100% Modulus | 0.0138 GPa | 2.00 ksi | ASTM D-638 |

| Thermal Properties | Metric | English | Comments |
|-------------------------|----------|---------|------------|
| Brittleness Temperature | -16.0 °C | 3.20 °F | ASTM D-746 |
| Oxygen Index | 36 % | 36 % | ASTM D-638 |

| Processing Properties | Metric | English | Comments |
|-----------------------|--------|---------|----------|
| Melt Temperature | 191 °C | 375 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China