

Axiall 28930 Coax & Telecom Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Non-lead stabilized 105C FT-4 riser jacket compound. UV resistant. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-28930-Coax-Telecom-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 - 1.43 g/cc	1.39 - 1.43 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90 - 96	90 - 96	delayed; ASTM D-2240
Tensile Strength, Yield	20.7 MPa	3000 psi	ASTM D-638
Elongation at Yield	190.4 %	190.4 %	Air Aging: 168 hours @ 136°C; 30 mil slabs; UL 1581
	280 %	280 %	ASTM D-638

Thermal Properties	Metric	English	Comments
Oxygen Index	33.5 %	33.5 %	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	193 °C	380 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China