

Axiall 390 Coax & Telecom Flexible PVC

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Buried service telecom jacket. Information provided by Georgia Gulf Georgia Gulf became Axiall Corporation in 2013.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Axiall-390-Coax-Telecom-Flexible-PVC.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 - 1.37 g/cc	1.33 - 1.37 g/cc	ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	86 - 92	86 - 92	delayed; ASTM D-2240
Tensile Strength, Yield	19.0 MPa	2750 psi	ASTM D-638
Elongation at Yield	301.75 %	301.75 %	Air Aging: 7 days @ 100°C; 75-mil plaques; UL 1581
	355 %	355 %	ASTM D-638
100% Modulus	0.01258 GPa	1.825 ksi	ASTM D-638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-33.0 °C	-27.4 °F	ASTM D-746
Oxygen Index	29 %	29 %	ASTM D-638

Processing Properties	Metric	English	Comments
Melt Temperature	188 °C	370 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China